

Rec'd PCT/PTO 18 JAN 2005

10/501511

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
24 July 2003 (24.07.2003)

PCT

(10) International Publication Number
WO 03/060234 A1

- (51) International Patent Classification⁷: **D21H 25/18**
- (21) International Application Number: PCT/EP02/00319
- (22) International Filing Date: 15 January 2002 (15.01.2002)
- (25) Filing Language: English
- (26) Publication Language: English
- (71) Applicant (*for all designated States except US*):
CONSORZIO INTERUNIVERSITARIO PER LO SVILUPPO DEI SISTEMI A GRANDE INTERFASE C.S.G.I. [IT/IT]; Piazza S. Marco, 4, I-50121 Firenze (IT).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): **BAGLIONI, Piero** [IT/IT]; Via Mimmole, 192/A, I-50010 Fiesole (IT). **DEI, Luigi** [IT/IT]; Via G. Carducci 16, I-50121 Firenze (IT). **GIORGI, Rodorico** [IT/IT]; Via Galcianese 105, I-59100 Prato (IT). **SCHETTINO, Claudius, Vinicius** [IT/IT]; Via Senese 303, I-50124 Firenze (IT).
- (74) Agent: **GERVASI, Gemma**; Notarbartolo & Gervasi S.p.A., Corso di Porta Vittoria, 9, I-20122 Milan (IT).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Declaration under Rule 4.17:**
— *of inventorship (Rule 4.17(iv)) for US only*
- Published:**
— *with international search report*
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: BASIC SUSPENSION, ITS PREPARATION AND PROCESS FOR PAPER DEACIDIFICATION

(57) Abstract: Basic suspension wherein oxides, hydroxides, carbonates, or their mixture, in the form of particles having determined dimensions are suspended in the appropriated solvents, are described. Processes for the preparation of the above said suspensions and of the suspended particles are also described together with the uses of the suspensions in processes for paper deacidification and/or porous materials consolidation.

WO 03/060234 A1

BASIC SUSPENSION, ITS PREPARATION AND PROCESS FOR PAPER DEACIDIFICATION

Field of the invention

The present inventions refers to basic suspensions which, thanks to their physico-chemical properties, can annul the acidity present in papers, which depends on
5 the paper production processes, on the environment pollution, and on the usage of acid inks as, for example, in the modern books.

State of the art

It is well known how the presence of acidity in paper is the main responsible of its
10 degradation with consequent loss of a lot of important information and in particular of historically important documents.

The acidity, which is present particularly in modern paper, forms during the paper manufacture, it is also a consequence of the use of acid inks (which are very common especially in the last centuries) or because of the adsorption of acid
15 pollutants which are present in the air.

Many different techniques and products have been studied or developed in order to eliminate acidity from paper and published documents (paper de-acidification). Unfortunately, up to now, the problem is far to be satisfactorily solved, and the specialists are intensively looking for new products capable of annulling the acidity
20 present in paper.

Calcium, magnesium, and barium hydroxide aqueous solutions have been widely used for many decades, but, unfortunately, they had often induced not desirable side effects, because of their strong alkaline conditions, with subsequent depolymerization of cellulose.

Non aqueous deacidification processes have also been proposed. In Smith R.D.,
Mass Deacidification at the Public Archives of Canada in Conservation of Library
and Archive Materials and the Graphic Arts, Butterworth Ed., London, 1987 the
use of magnesium alkoxide deacidification solutions (Wei T'o method) is
5 described; another method widely used is the Bookkeeper method which is based
on the application of suspended MgO that, subsequently converted in magnesium
hydroxide, forms the alkaline reservoir. Unfortunately, these methods use
chlorofluorocarbon (CFC) solvents. Alternatively, some solvent mixtures have
been recently experimented, as thrielyne (90%) and methanol, but all of them are
10 harmful.

Despite of its scarce usage, calcium hydroxide is an excellent deacidifying agent.
Calcium hydroxide is physico-chemically friendly to most of papers and, once
converted to calcium carbonate, works efficiently as alkaline reservoir. In IT
1.286.868 (in the name of the same Applicant) it is reported that suspensions of
15 calcium hydroxide could be used to consolidate mural paintings and to deacidify
paper. However, the calcium hydroxide suspensions in organic solvent described
in this document were obtained from lime and the particle size distribution was
quite broad and larger than several micrometers. Smaller particles were around
0.5 microns, 80% were greater than 1 micron. This originated two problems: firstly,
20 kinetic stability was good but not excellent for some application procedures, for
example spraying; secondly, because of particle sizes, a white glaze (or spots) on
the treated surfaces could form.

Large calcium hydroxide particles showed a poor adhesions and penetrability into
the cellulosic fibres.

Deacidifying agents must ensure good adhesion with fibres, so that the alkaline reservoir acts efficiently. Therefore, according to physico-chemical features of cellulose, particles with a surface charge density are preferred. Both these requirements are ensured by the use of particles smaller than micron size.

5 Summary of the invention

The present invention refers to basic suspension wherein the suspended particles have determined dimensions, moreover the invention refers to process for the preparation of the suspensions and of the suspended particles and to the use of the suspension in processes of paper deacidification and porous materials
10 consolidation.

Detailed description of the invention

The present invention makes it available basic suspension which allow the overcoming of the problems connected with paper acidity.

The suspension according to the inventions are preferably suspensions of basic
15 oxides or hydroxides (which are capable of forming carbonates when in contact with the CO₂ of the air or to form, once adsorbed on the treated material, a reservoir of basicity stable for long periods of time) or basic carbonates or their mixture.

Particularly preferred according to the invention are the oxides, hydroxides or
20 carbonates of alkali or earth-alkali metals or also other analogous compounds having basic properties.

Examples of compounds suitable for the suspensions according to the invention are: Li₂O, Na₂O, K₂O, MgO, CaO, SnO, SnO₂, PbO, Pb₂O, Pb₂O₃, BiO, Bi₂O₃, Sb₂O₃, LiOH, NaOH, KOH, Mg(OH)₂, Ca(OH)₂, Al(OH)₃, Sn(OH)₂, Sn(OH)₄,

Pb(OH)_2 , Bi(OH)_3 , Sb(OH)_3 , Li_2CO_3 , Na_2CO_3 decahydro, Na_2CO_3 , K_2CO_3 , MgCO_3 , CaCO_3 , PbCO_3 , anhydro and basic, $\text{Bi}_2\text{O}_2\text{CO}_3$ or their mixtures.

Particularly preferred according to the invention are the suspensions of Mg(OH)_2 , Ca(OH)_2 , Sn(OH)_2 .

- 5 The preferred suspending solvents are chosen in the group consisting of: water, ethyl ether, acetone, alcohols, and their mixtures.

Among the alcohols particularly preferred are: methanol, ethanol, 1-propanol, 2-propanol, butanol, pentanol, and their mixtures.

- Particularly preferred are suspension of the Ca(OH)_2 hydroxide in 1% (w/w) in
10 water and 99% in 1-propanol (or 2-propanol).

- The dimensions of the hydroxide particles in suspension play also a crucial role in the suspensions according to the invention. In fact, such particles must be capable of entering the fibres of the materials to treat, linking with them, without covering effect over the written text since this would produce a not desirable aesthetically
15 effect. Large particles need longer time to penetrate in depth, but the fast volatilisation of used organic solvents does not usually allow it. Therefore, a strict control of particle size is essential before the application.

- Particularly preferred are suspensions according to the invention wherein the suspended particles have dimension comprised between 10nm up to $2\mu\text{m}$, more
20 preferably between 50nm up to 500nm.

The suspensions according to the invention have a concentration of suspended particles in the solvent preferably comprised between: 0.1-50 g/L more preferably between 1-25 g/L.

Especially preferred is a concentration of: 10 g/L.

The suspensions according to the invention can be obtained by vigorous stirring of the particles to be suspended in the appropriate solvent (or solvents mixture), if necessary with the aid of a sonicator or ultra-sonicator or with the aid of a homogeniser.

- 5 The particles to be suspended, having the desired measures, can be obtained by high temperature homogeneous phase reaction, heterogeneous phase reaction (slaking of oxides), and by mixing two water in oil microemulsion obtaining a low solubility salt in nanosized aqueous core.

10 The first process consists in reacting solutions of the appropriate reagents (for example a solution of an hydroxide as NaOH and a solution of a chloride as CaCl_2) at high temperature (about 90°C) under stirring.

The solutions to be reacted can be obtained by solving the reagents in a solvent chosen in the group consisting of: water, a solution of diols or a mixture water/diols (the reagents can be solved both in the same or each one in a different solvent
15 chosen from the above said group).

The preferred diols are C_{1-6} alkane diols as, for example, 1,2 ethandiol or 1,2 propandiol.

The suspension obtained after reaction at high temperature and containing the formed particles is cooled down to room temperature under N_2 , the supernatant
20 solution is eliminated and the suspension is washed to eliminate secondary reaction products and concentrated in vacuum to form a paste which can be suspended again in the desired solvent amount.

According to the slaking of oxides process the oxide is slaked in pure water, the obtained hydroxide paste is mixed with an alcohol under vigorous stirring and sonicated or homogenised.

Alternatively, according to known techniques, two water in oil microemulsions are prepared wherein the aqueous phase containing salts, when the two microemulsions are mixed precipitation takes place wherein the nanosized dimensions of the aqueous drops impose limited growth of particles.

Given the above said, examples of suspensions according to the invention are reported hereinafter in order to better illustrate the invention:

10 **Example 1**

Calcium hydroxide micro-particles have been obtained by slaking CaO powder in pure water, at room temperature:

- CaO powder 10 g
- Water 30 g

15 Successively, suspensions have been prepared by mixing the calcium hydroxide paste with alcohol, under vigorous stirring, and have been sonicated for 30 minutes with an ultra-sonicator for further reducing the particle size and obtaining a complete dispersion of the calcium hydroxide agglomerates. A homogeniser system, for preparation of some hydroxide dispersions, can also be used.

20 **Example 2**

Calcium hydroxide micro-particles have been obtained by slaking CaO powder in water/alcohol mixtures, according to the following proportions:

- CaO powder 1 g
- Water 5 g

- 1-propanol 25 mL

The metal oxide/water/alcohol mixture, after 30 minutes of sonication or vigorous stirring has been left to rest at least 8 hours. Suspensions have been prepared by mixing the calcium hydroxide paste, after filtration, with alcohol, under vigorous stirring. Suspensions have been sonicated for 30 minutes with an ultra-sonicator for further reducing the particle size and obtaining a complete dispersion of the calcium hydroxide agglomerates. A homogeniser system, for preparation of some hydroxide dispersions, was also necessary.

Example 3

Calcium hydroxide nanoparticles, from homogeneous phase reaction, have been achieved by mixing a NaOH aqueous solution with a CaCl_2 aqueous solution. They were previously heated up to a selected temperature (around 90 °C), under continuous stirring and keeping the temperature of the mixture constant within ± 1 °C; the supersaturating degree was kept in the range 2-10. Aqueous $\text{Ca}(\text{OH})_2$ suspension was allowed gradually reaching the room temperature under a nitrogen atmosphere to avoid the $\text{M}(\text{OH})_2$ carbonation. The supernatant solution was discarded and the remaining suspension was washed five times with water to reduce the NaCl concentration below 10^{-6} M. Each time, the dilution ratio between the concentrated suspension and the washing solution was about 1:10. The complete removal of NaCl from the suspension was controlled by the AgNO_3 test. The suspension was then concentrated in vacuum at 40 °C up to a weight ratio $\text{M}(\text{OH})_2/\text{water}$ of 0.8, that is the same of the standard slaked lime paste. Dispersions have been prepared by mixing 10g of the calcium hydroxide paste with 1L of alcohol, under vigorous stirring, and/or by using a homogeniser.

Example 4

Calcium hydroxide nanoparticles, from homogeneous phase reaction, have been obtained by mixing a NaOH aqueous solution with a CaCl_2 diol solution (i.e. 1,2 ethandiol or 1,2 propandiol). Diol solution was previously heated up to a selected temperature (around 150 °C), under continuous stirring and keeping the temperature of the mixture constant within ± 1 °C; the supersaturating degree was in the range 2-10. The NaOH aqueous solution was added dropwise to diol solution keeping the temperature around 150°C. The Ca(OH)_2 water/diol suspension was allowed gradually reaching the room temperature under a nitrogen atmosphere to avoid the M(OH)_2 carbonation. The supernatant solution was discarded and the remaining suspension was washed five times with water to reduce the NaCl concentration below 10^{-6} M. Each time, the dilution ratio between the concentrated suspension and the washing solution was about 1:10. The complete removal of NaCl from the suspension was controlled by the AgNO_3 test. Then, water/diol suspension was washed several times with 2-propanol to remove diol solvents. Successively, solutions were concentrated in vacuum at 40 °C up to a weight ratio $\text{M(OH)}_2/\text{water}$ of 0.8, that is the same of the standard slaked lime paste. Dispersions have been prepared by mixing 10g of the calcium hydroxide paste with 1L of alcohol, under vigorous stirring, and/or by using a homogeniser.

Example 5

Two water in oil microemulsions have been obtained.

C_{12}E_4 surfactant solutions in cyclohexane have been prepared and used as oil phase in the microemulsion. These solutions have been mixed with NaOH (0.1M) and CaCl_2 (0.05M) aqueous solution.

Microemulsion (water in oil) composition is:

- $C_{12}E_4$ 0.15 g (0.2M)
- Cyclohexane 1.15 g
- NaOH (0.1M) and $CaCl_2$ (0.05M) aqueous solution 25 μ L (w=2)

5 Water/surfactants molar ratio ranging (molar ratio w=water/surfactant) from 1 to 5.

Aqueous solution was added to oil phase/surfactant solution by a microsyringe.

The preparation was held at 15°C. Similar isotropic, transparent, and stable systems, were obtained in a wider temperature range, 15-25°C. Microemulsions

have been equilibrated at 15°C for 10 days. Crystallization processes took place

10 within the confined volume of the microdroplets. Synthesized particles, after filtration, washing, and drying have been dispersed in nonaqueous solvents, by vigorous stirring and/or with the aid of a homogeniser.

Example 6

Solution of Igepal CO 520 in cyclohexane (0.15M) has been prepared and mixed,
15 respectively, with an aqueous solution of NaOH (0.5M) and with an aqueous solution of $CaCl_2$ (0.25M).

Microemulsion (water in oil) composition is:

- Igepal CO 520 solution (0.15M) 1 g
- NaOH (0.5M) and $CaCl_2$ (0.25M) aqueous solution 25 μ L (w=2)

20 Water/surfactants molar ratio ranging (molar ratio w=water/surfactant) from 1 to 11.

Aqueous solution was added to oil phase/surfactant solution by a microsyringe.

The preparation was held at environmental (25°C). Analogous systems, isotropic,

transparent, and stable was obtained in a wider temperature range, 15-25°C.

Microemulsions have been equilibrated at 25°C for a week.

Synthesized particles, after filtration, washing, and drying have been dispersed in nonaqueous solvents, by vigorous stirring and/or with the aid of a homogeniser.

5 Procedures for application

The physico-chemical properties of the prepared dispersions make them very attractive for different application procedures in paper deacidification processes, such as:

- spraying,
- 10 • immersing,
- brushing,
- mass-deacidification process.

Small particle dimensions allows using a sprayer without risks of hole occlusion.

The spraying method is preferred.

- 15 The complete immersion of paper sheet is possible also for longer period. Aqueous deacidification methods, because of the strong aggressive effect of high pH, do not allow a long contact with paper sheet, commonly up to 20 minutes. This produces only a poor deacidification effect.

- Moreover the basic suspensions according to the invention can be used also for
20 the consolidation of porous materials as for example stones, plasters building materials and similar.

Claims

- 1) Basic suspension wherein the suspended particles have dimensions comprised between 10nm up to 2 μ m.
- 2) Basic suspensions according to claim 1 wherein the suspended particles have dimensions comprised between 50nm up to 500nm.
- 3) Basic suspensions according to claims 1 and 2 wherein the suspended particles are basic oxides or hydroxides or carbonates or their mixture.
- 4) Basic suspensions according to claim 3 wherein the suspended basic oxides are chosen in the group consisting of: Li₂O, Na₂O, K₂O, MgO, CaO, SnO, SnO₂, PbO, Pb₂O, Pb₂O₃, BiO, Bi₂O₃, Sb₂O₃ or their mixtures.
- 5) Basic suspensions according to claim 3 wherein the suspended basic hydroxides are chosen in the group consisting of : LiOH, NaOH, KOH, Mg(OH)₂, Ca(OH)₂, Al(OH)₃, Sn(OH)₂, Sn(OH)₄, Pb(OH)₂, Bi(OH)₃, Sb(OH)₃ or their mixtures.
- 6) Basic suspensions according to Claim 3 wherein the suspended basic carbonates are chosen in the group consisting of: Li₂CO₃, Na₂CO₃ deca-hydro, Na₂CO₃, K₂CO₃, MgCO₃, CaCO₃, PbCO₃, anhydro and basic, Bi₂O₂CO₃ or their mixtures.
- 7) Basic suspensions according to Claims 1 – 6 wherein the solvents are chosen in the group consisting of: water, ethyl ether, acetone and alcohols and their mixtures.
- 8) Basic suspension according to claim 7 wherein the alcohols are chosen in the group consisting of: methanol, ethanol, 1-propanol, 2-propanol, butanol, pentanol, and their mixtures.

9) Basic suspension according to Claims 1 – 8 consisting of: $\text{Ca}(\text{OH})_2$ hydroxide particles suspended in 1% water and 99% 1-propanol or 2-propanol (w/w).

10) Process for the preparation of the suspensions according to Claims 1 – 9 by vigorous stirring of the particles to be suspended in the appropriate solvent (or solvents mixture), if necessary with the aid of a sonicator or ultra-sonicator or with the aid of a homogeniser

11) Process according to Claim 10 wherein the particles to be suspended are obtained by high temperature homogeneous phase reaction.

12) Process according to Claim 10 wherein the particles to be suspended are obtained by slaking of the oxides.

13) Process according to Claim 10 wherein the particles to be suspended are obtained by mixing two water in oil microemulsions, giving a low solubility salt in nanosized aqueous core.

14) Use of the suspension according to claims 1- 9 in paper deacidification processes, as neutralising agent and also as alkaline reservoir.

15) Process for paper deacidification wherein suspensions according to claims 1 - 9 are applied to the papers to be deacidified by: spraying, immersing, brushing, or by mass-deacidification process.

16) Use of the suspensions according to Claims 1 – 9 in processes for the consolidation of porous materials.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/00319

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 D21H25/18

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 D21H

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 1 001 084 A (ZFB ZENTRUM FUER BUCHERHALTUNG) 17 May 2000 (2000-05-17)	1-8, 14, 15
Y	column 6, line 55 -column 8, line 22; claims 1-6	13
Y	EP 0 543 372 A (SYREMONT SPA) 26 May 1993 (1993-05-26) claims 1-15; examples 1-4	13
Y	EP 1 134 302 A (CONSORZIO INTERUNIVERSITARIO P) 19 September 2001 (2001-09-19) claims 1-13; examples 1,2	13
X	US 4 522 843 A (KUNDROT ROBERT A) 11 June 1985 (1985-06-11) claims 1-24; examples 6,7	1, 3-5, 7, 8, 14, 15
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the International filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the International filing date but later than the priority date claimed

- *T* later document published after the International filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- * & * document member of the same patent family

Date of the actual completion of the international search

11 June 2002

Date of mailing of the international search report

19/06/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Karlsson, L

INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/00319

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with Indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 6 080 448 A (BURD JAMES E ET AL) 27 June 2000 (2000-06-27) column 3, line 16 -column 4, line 48; claims 1-17 ----	1,4,5, 14,15
X	WO 99 01377 A (KEMPRO ITALIANA S R L ;TODARELLO FRANCESCO (IT)) 14 January 1999 (1999-01-14) claims 1-16 ----	1,7
X	US 6 235 150 B1 (SCALLAN ANTHONY M ET AL) 22 May 2001 (2001-05-22) claims 1-26 ----	1
A	US 6 025 034 A (BOLAND ROSS F ET AL) 15 February 2000 (2000-02-15) claims 1-13; examples 1-8 ----	1-16
A	EP 1 111 128 A (UNIV CATALUNYA POLITECNICA) 27 June 2001 (2001-06-27) the whole document ----	1-16
A	US 5 433 827 A (PAGE DEREK H ET AL) 18 July 1995 (1995-07-18) the whole document -----	1-16



INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/EP 02/00319

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 1001084	A	17-05-2000	DE 19921616 A1 EP 1001084 A2	18-05-2000 17-05-2000
EP 0543372	A	26-05-1993	IT 1252006 B CA 2083460 A1 EP 0543372 A1 JP 6015161 A	27-05-1995 21-05-1993 26-05-1993 25-01-1994
EP 1134302	A	19-09-2001	EP 1134302 A1	19-09-2001
US 4522843	A	11-06-1985	CA 1235555 A1 FR 2578198 A1 GB 2171122 A , B	26-04-1988 05-09-1986 20-08-1986
US 6080448	A	27-06-2000	AU 743868 B2 AU 3205099 A CA 2326998 A1 EP 1068395 A1 JP 2002510758 T WO 9951819 A1 US 6342098 B1	07-02-2002 25-10-1999 14-10-1999 17-01-2001 09-04-2002 14-10-1999 29-01-2002
WO 9901377	A	14-01-1999	IT RM970391 A1 AT 208739 T AU 8802998 A CN 1261860 T DE 69802538 D1 DE 69802538 T2 WO 9901377 A1 EP 0996588 A1	04-01-1999 15-11-2001 25-01-1999 02-08-2000 20-12-2001 23-05-2002 14-01-1999 03-05-2000
US 6235150	B1	22-05-2001	AU 2708799 A BR 9909003 A CA 2324459 A1 WO 9949133 A1 EP 1068391 A1 JP 2002507675 T	18-10-1999 28-11-2000 30-09-1999 30-09-1999 17-01-2001 12-03-2002
US 6025034	A	15-02-2000	US 2001004473 A1 US 2002031658 A1 CA 2237588 A1 CN 1175984 A EP 0866885 A1 WO 9718341 A1	21-06-2001 14-03-2002 22-05-1997 11-03-1998 30-09-1998 22-05-1997
EP 1111128	A	27-06-2001	ES 2151835 A1 ES 2151836 A1 AU 5290699 A BR 9912591 A EP 1111128 A2 WO 0008250 A2	01-01-2001 01-01-2001 28-02-2000 16-10-2001 27-06-2001 17-02-2000
US 5433827	A	18-07-1995	CA 2138445 A1	22-06-1995